

CERTIFICATE of Compliance

TRADE NAME: USA 7018-1 Specification: AWS A 5.1 : ASME SFA 5.1 Classification: E7018-1

Chemical Composition for Weld Metal

	AWS Requirements	Typical
Carbon (C)	0.15 max.	0.065
Manganese (Mn)	1.60 max.	1.35
Silicon (Si)	0.75 max.	0.63
Phosphorus (P)	0.035 max.	0.020
Sulfur (S)	0.035 max.	0.004
Nickel (Ni)	0.30 max.	0.027
Chromium (Cr)	0.20 max.	0.018
Molybdenum (Mo)	0.30 max.	0.015
Vanadium (V)	0.08 max.	0.016
Mn + Ni + Cr + Mo + V	1.75 max.	

Mechanical Properties for Weld Metal

	Minimum AWS Requirements	Typical
Tensile Strength	70,000 psi	86,000 psi
Yield Strength	58,000 psi	70,000 psi
Elongation in 2"	22 %	31 %
Charpy V-notch Impact Average	20 ft [·] lbs at -50°F	91 ft [·] lbs at -50°F

This certification is provided by Washington Alloy Co. with the expressed understanding that if the product supplied fails to conform the stated specifications, there shall be no personal liability of any kind on the undersigned and the obligation and liability of Washington Alloy Co., with respect to such non-conformance or specification failure, shall be limited to a) an obligation to furnish the purchaser, at no additional charge, material that meets the specifications and conformances or b) to refund to the purchaser the full amount of money paid to Washington Alloy Co. for the return of the product in full. In no event shall Washington Alloy Co. be liable for consequential damage.

This certifies that the product supplied will meet the requirements of the noted classification and data above. Products supplied in accordance to the Quality Management System of Washington Alloy Company.

Certification Administrator

EAST COAST 7010-G Reames Rd Charlotte, NC 28216 Tel (888) 522-8296 Fax (704)598-6673 GULF COAST 4855 Alpine Drive #190 Stafford, TX 77477 Tel (877) 711-9274 Fax (281)313-6332 WEST COAST 8535 Utica Ave Rancho Cucamonga, CA 91730 Tel(800)830-9033 Fax (909)291-4586



Warehouse Distribution Center - Dayton, Ohio

Head Office – Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.