



WASHINGTON ALLOY'S Quality
Management System is
Certified to ISO 9001:2008
Cert # 05-R0925

70T-1 Carbon Steel Flux-Cored Wire

U.S. ALLOY CO.
dba Washington Alloy
7010-G Reames Rd.
Charlotte, NC 28216
www.weldingwire.com



ALLOY DESCRIPTION AND APPLICATION;

70T-1 is a flux cored wire designed for single or multi pass welding having a spray-type transfer, low spatter loss, flat to slightly convex bead contour, with a moderate volume of slag completely covering the weld bead. With its high deposition rate and easily removal slag it is a good choice for mild steel as well as low alloy steels.

TYPICAL FCAW WELDING PROCEDURES; DCEP OPTIMUM IN BOLD (FLAT)

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Electrical Stickout
0.052	150- 400 -600	140- 275 -390	19- 28 -35	1/2-1"
1/16"	150- 330 -490	150- 330 -475	23- 30 -38	1/2-1"
5/64"	120- 250 -300	250- 385 -450	26- 29 -32	3/4-1 1/4"
3/32"	110- 185 -275	300- 425 -550	25- 29 -34	3/4-1 1/4"
1/8"	70- 110 -200	380- 525 -775	27- 30 -37	3/4-1 1/4"

Procedures may vary with change in position, base metals, filler metals, equipment and other changes.

TYPICAL WELD METAL CHEMISTRY (%) AND WELD METAL PROPERTIES;

	AWS Spec.	U.S. ALLOY 70T-1	BASED ON 100% CO ₂	AWS Spec	Typical
Carbon	0.12 max	0.03		70-95,000	82,500
Manganese	1.75 max	1.45	Tensile Strength (psi)	58,000 min.	78,000
Silicon	0.90 max	0.50	Yield Strength (psi)	22 % min.	25%
Phosphorus	0.030 max.	0.014	Elongation in 2"	20 ft-lbs min.	37 ft-lbs
Sulfur	0.030 max.	0.013	Charpy V-notch at 0°F		

AVAILABLE SIZES: TCF 70T-1= Spools of 1/16, 5/64, 3/32, 1/8

SPECIFICATIONS; ANSI/AWS A5.20 E70T-1
ASME SFA A5.20 E70T-1

EAST COAST
7010-G Reames Rd
Charlotte, NC 28216
Tel (888) 522-8296
Fax (704)598-6673

GULF COAST
4755 Alpine Drive #100A
Stafford, TX 77477
Tel (877) 711-9274
Fax (281)313-6332

WEST COAST
8535 Utica Ave
Rancho Cucamonga, CA 91730
Tel(800)830-9033
Fax (909)291-4586



2012 DC

Warehouse Distribution Center – Dayton, Ohio

Head Office – Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.