

EACT COACT

## 71T-11 Carbon Steel Gasless Welding Wire

U.S. ALLOY CO. dba Washington Alloy 7010-G Reames Rd. Charlotte, NC 28216 www.weldingwire.com





## ALLOY DESCRIPTION AND APPLICATION;

71T-11 is a self-shielding flux cored wire designed for single or multi pass welding having a smooth spray-type transfer commonly used on mild steels less than 3/4" thick. Easy general all position wire to use in the field where shielding gas is not practical. Limit to three passes will ensure properties on the mechanicals and weld deposit chemistry.

## TYPICAL FCAW WELDING PROCEDURES; DCEN

Wire Diameter	Wire Speed (ipr	n) Amps	Volts	Electrical Stickout
0.030	60 <b>-175</b> -200	30 <b>-115</b> -200	14- <b>15</b> -18	3/8-1/2
0.035	40 <b>-210</b> -240	50 <b>-150</b> -220	13 <b>-17</b> -19	3/8-1/2
0.045	50 <b>-170</b> -200	80 <b>-180</b> -220	13 <b>-17</b> -20	3/8-5/8
1/16"	60 <b>-100</b> -180	120 <b>-185</b> -300	15 <b>-16</b> -20	1/2-1"

Procedures may vary with change in position, base metals, filler metals, equipment and other changes.

## TYPICAL WIRE CHEMISTRY (%) AND WELD METAL PROPERTIES;

	AWS Spec.	U.S. ALLOY 7	71T-11		
Carbon	0.30 max	0.10		AWS Spec	Typical
Manganese	1.75 max	0.55	Tensile Strength (psi)	70-95,000	77,000
Silicon	0.60 max	0.10	Yield Strength (psi)	58,000 min.	70,000
Aluminum	1.80 max	1.20	Elongation in 2"	20% min.	22%
Phosphorus	0.030  max.	0.016			
Sulfur	0.030 max.	0.006			

**AVAILABLE SIZES**: TW 71T-11= Spools of .030, .035,.045, .068, 1/16, 5/64

CITECOACT

**SPECIFICATIONS**; **ANSI/AWS** A5.20 E71T-11 **ASME SFA** A5.20 E71T-11



EAST COAST	GULF COAST	WEST COAST 2012 DC
7010-G Reames Rd	4755 Alpine Drive #100 A	8535 Utica Ave
Charlotte, NC 28216	Stafford, TX 77477	Rancho Cucamonga, CA 91730
Tel (888) 522-8296	Tel (877) 711-9274	Tel(800)830-9033
Fax (704)598-6673	Fax (281)313-6332	Fax (909)291-4586

Warehouse Distribution Center – Dayton, Ohio Head Office – Puyallup, Washington

WEST COAST

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.