

Quality Management System in accordance with ISO 9001:2000 Cert # 05-R0925

## CERTIFICATE of Compliance

TRADE NAME: USA 8018-C1 Specification: AWS A 5.5 : ASME SFA 5.5

Classification: E8018-C1



dba Washington Alloy 7010-G Reames Rd. Charlotte, NC 28216 www.weldingwire.com



## Chemical Composition for Weld Metal

AWS Requirements	Typical
0.12 max.	0.060
1.25 max.	0.980
0.80 max.	0.600
0.03 max.	0.013
0.03 max.	0.007
2.00-2.75	2.41
	·
	0.12 max. 1.25 max. 0.80 max. 0.03 max. 0.03 max.

## Mechanical Properties for Weld Metal

	AWS Requirements min.	Typical 1)
Tensile Strength	80,000 psi	87,000 psi
Yield Strength	67,000 psi	73,000 psi
Elongation in 2"	19 %	32 %
Charpy V-notch Impact Average	20 ft · lbs at -75°F	94 ft ·lbs at -75°F

This certification is provided by Washington Alloy Co. with the expressed understanding that if the product supplied fails to conform the stated specifications, there shall be no personal liability of any kind on the undersigned and the obligation and liability of Washington Alloy Co., with respect to such non-conformance or specification failure, shall be limited to a) an obligation to furnish the purchaser, at no additional charge, material that meets the specifications and conformances or b) to refund to the purchaser the full amount of money paid to Washington Alloy Co. for the return of the product in full. In no event shall Washington Alloy Co. be liable for consequential damage.

This certifies that the product supplied will meet the requirements of the noted classification and data above. Products supplied in accordance to the Quality Management System of Washington Alloy Company.



1) As Welded

EAST COAST
7010-G Reames Rd
Charlotte, NC 28216
Tel (888) 522-8296
Fax (704)598-6673
GULF COAST
4855 Alpine Drive #190
Stafford, TX 77477
Tel (877) 711-9274
Fax (281)313-6332

WEST COAST 8535 Utica Ave Rancho Cucamonga, CA 91730 Tel(800)830-9033 Fax (909)291-4586

Warehouse Distribution Center – Dayton, Ohio

Head Office – Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.