

SUPERFLOW[®] 94/6 Tin/Silver

U.S. ALLOY CO. dba Washington Alloy 7010-G Reames Rd. Charlotte, NC 28216 www.weldingwire.com American Welding Society Sustaining Company Member

ALLOY DESCRIPTION AND APPLICATION:

SUPERFLOW[®] 94/6 - Silver Bearing Solders has excellent strength with high elongation and vibration resistance for sound joints in many applications. With its low melting temperature and bonding of all the ferrous and non-ferrous alloys including stainless steel, nickel, copper tubing, brass, etc - this alloy will prevent distortion and loss of your base metal properties. On copper tubing it will give a stronger overall finished assembly than the typical braze alloys. 94/6 has a high silver content than our other Sn/Ag solder giving it a plastic range of 105° F which may be useful in poor fit up & wide clearance.

CHEMICAL COMPOSITION, Weight Percent:

Silver Tin

PHYSICAL DATA:

Color Solidus Liquidus Electrical Conductivity Elongation Tensile Strength¹ Shear Strength¹ 5.4-6.0 % Remainder

> Bright Silver 430°F (221°C) 535°F (221°C) 17.1 49% 15,000 psi 13,500 psi

¹Copper solder joint

AVAILABLE SIZES:

TAS 94/6Ag = 1# Spools of 1/16, 3/32 & 1/8 and 5# Spools of 3/32Other sizes available – please inquire

SPECIFICATIONS:

Washington Alloy

EAST COAST	(
7010-G Reames Rd	4
Charlotte, NC 28216	
Tel (888) 522-8296	7
Fax (704)598-6673]

GULF COAST 4755 Alpine Drive #100A Stafford, TX 77477 Tel (877) 711-9274 Fax (281)313-6332 WEST COAST 8535 Utica Ave Rancho Cucamonga, CA 91730 Tel(800)830-9033 Fax (909)291-4586



DC 2012

Warehouse Distribution Center - Dayton, Ohio

Head Office - Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part .